



Element Materials Technology
15062 Bolsa Chica
Huntington Beach, CA
92649-1023 USA

P 714 892 1961
F 714 892 8159
T 888 786 7555
info.hb@element.com
element.com

Contact: John Wong
Virina Steel
211 Yacht Club Way
Redondo Beach, CA 90277

TEST CERTIFICATE — EAR-CONTROLLED DATA

Date: 7/18/2019
Purchase Order Number: VERBAL
Work Order Number: VIR004-06-11-27129-1

Specification:	ASTM A1035-16b GR. 130
Description:	Re-Bar (10x60mm)

REBAR TENSILE					
Test Method: ASTM A370-18					
Requirement: INFO ONLY					
Sample Number	Area	Bar Size	UTS (PSI / LBS)	Yield (PSI / LBS)	8 inch Elongation In %
1	.2000	4	140,000 / 28,096	103,000 / 20,669	7.0

BEND TEST

Test Method: ASTM E 290-14
Material Diameter: 0.500"
Bend Factor 3.5
Mandrel Diameter: 1.750"
Bend Angle: 180°
Without cracking on the outside radius of the bent portion.
(1) ACCEPTABLE

CONFORMS TO REQUIREMENTS

This document contains technical data whose export and re-export/ retransfer is subject to control by the U.S. Department of Commerce under the Export Administration Act and the Export Administration Regulations. The Department of Commerce's prior written approval may be required for the export or re-export/retransfer of such technical data to any foreign person, foreign entity or foreign organization whether in the United States or abroad.

Respectfully submitted


Kelly Nguyen
Senior Quality Administrator

15062 Bolsa Chica, Huntington Beach, CA 92649
(714) 892-1961 ph • (714) 892-8159 fax www.element.com

Denotes non-conforming results. *Denotes change made from original test certificate.
The information contained in this certification represents only the material submitted and is certified only for the quantities tested. Reproduction except in full is reserved pending written approval. The recording of false, fictitious, or fraudulent statements or entries on the certificate may be punishable as a felony under federal law. All testing was performed in a mercury free environment. All testing performed in accordance with the latest edition of the applicable ASTM, or other Federal Test Method in effect at the time of test.